

Test Report No 210077-6

Aim of Testing: quality control according to the requirements of the federal specification TT-P-1952F (17 FEB 2015) for paint, traffic and airfield marking, waterborne

LIMBOROUTE LW48F Airport, Federal Standard 595C 33538

Characteristic	Test method	Requirement		Test result
		Min	Max	
Yellow color match (CIE illuminant D65)	ASTM D1729-16 + TT-P-1952-F, 4.3.9.4	appropriate color match to Federal Standard 595 color number 33538		similar to standard, slightly lighter
Accelerated weathering (400 µm wet-film thickness, 300 h, UVB-313)	ASTM G154-16 + TT-P-1952-F, 4.3.10			
Yellow color match after accelerated weathering	ASTM D1729-16 + TT-P-1952-F, 4.3.9.4	appropriate color match to Federal Standard 595 color number 33538		similar to standard
Volatile organic content (VOC)	ASTM D2369-20		150 g/l	32.5 g/l
Consistency	ASTM D562-10	80 KU	90 KU	86 KU
Solids by volume	ASTM D2697-03	60 %		62.8 %
Dry opacity (300 µm wet-film thickness)	ASTM D2805-11 + TT-P-1952-F, 4.3.11	0.92		0.99
Dry time (no pick up)	ASTM D711-20		10 min	8 min
Fineness of dispersion	ASTM D1210-05	3.0 Hegman		> 7.5 Hegman
Bleeding ratio	ASTM D868-21	0.95		1.00
Pigment by weight	ASTM D3723-05	60 %	62 %	61 %

Magdeburg, 16.03.2021
iLF Magdeburg GmbH



Dr. Ute Holzhausen
Head Material Analytics



Dipl.-Ing. (FH) Tobias Böttge
Person in Charge

The test results refer only to the subjects of testing. The publication of the results in extracts is subject to the approval of the iLF Magdeburg GmbH. This test report is a shortened test report that does not cover all test conditions required by the applicable standards.