

SWARCOTHERM ALKYD BINDER

THERMOPLASTIC PAVEMENT MARKING COMPOUND

SPECIFICATION: Black



PRODUCT COMPOSITION

A blend of glycerol ester of rosin, high boiling point plasticizers, inert fillers, high friction aggregate and low-dust encapsulated black pigment

Binder 18 % min

PHYSICAL PROPERTIES

- **Specific Gravity** 2.15 max
- **Softening Point** 180 F° min
- **Bond Strength** 300+ psi
- **Drying Time** Less than 15 min at ambient temp of 90° F

STORAGE

Keep product dry. Store at temperatures of less than 100° F. Protect from direct sunlight with protective covering. Shelf life is 12 months.

All statements, technical information and recommendations contained herein are based on tests we believe to be reliable but the accuracy and completeness thereof is not guaranteed. Data is subject to alteration due to technical advances.

Above information not to be taken as a warranty or representation for which we assume legal responsibility. It is offered solely for consideration, investigation and verification.

If you have any questions about proper application techniques or other technical support issues, please contact your SWARCO sales or customer service representative.