

TECHNICAL INFORMATION
AGGLOTHERM TS



AGGLOTHERM TS

Status: 02.09.2020

1	Main characteristics / field of application	3
2	Technical information	3
3	Processing instructions.....	4
3.1	Preparing the material and application technique	4
3.1.1	Preparing the thermoplastic.....	4
3.1.2	Preparing the application technique	4
3.2	Optimising the processability of the material	4
4	Surfaces / surface pre-treatment	5
4.1	General information	5
4.2	Concrete or cement-bound surfaces	5
4.3	Bituminous surfaces	6
4.4	Paved surfaces.....	6
4.5	Synthetic resin floors	6
5	Application technique	7
6	Warranties / test certificates.....	7
6.1	Warranties	7
6.2	Table 1: Turntable road-marking test system (RPA) - test certificates of BAST	8

Important information:

Please note our general terms and conditions and general information on the technical information. We assume no liability for errors and misprints. The explanations provided in this information correspond to our best knowledge and experience. However, the information does not represent any assurance of properties. The information is passed on without liability, also with regard to any existing third-party property rights. The suitability for the intended purpose must be reviewed by the user at their own responsibility prior to use.

1 Main characteristics / field of application

AGGLOTHERM TS...

- belongs to the group of thermoplastic materials and is processed as an agglomerate marking
- thrives like all thermoplastics from wear and tear caused by roll-overs and the exposure of premix beads
- is approved with multiple test certificates by the Federal Highway Research Institute (BAST) as a type II marking, including in a system combination with the LIMBOROUTE 2-C K809
- is highly suitable for all bituminous surfaces and suitable for concrete surfaces (with primer)
- can be applied with standard thermoplastic laying machines with extruder technology for the laying of regular agglomerates
- thanks to the open structure of the agglomerate marking, possesses an excellent drainage effect in rain
- produces sound effects when being driven over and is therefore not suitable for built-up areas

2 Technical information

Colour	white
Density	approx. 1.990 kg/l +/- 0.1
Softening point	approx. 98°C
Flash point	above 240°C
Solvent content	solvent-free
Storage stability	6 months in original packaging; protect against frost, moisture and direct sunlight
Trafficability / Cool-off time	A few minutes after application, depending on the air and surface temperature. The markings must be inspected for their trafficability before being released for traffic.
Standard packaging	AGGLOTHERM TS: Powder goods in meltable PE bags on Euro pallets with 1,080 kg The PE bags are part of the recipe and are also melted in the thermal cooker. Drop-on material: Paper bags with PE inlay - 25 kg filling weight
Labelling	The applicable regulations and instructions for proper transport, handling and storage, first aid, toxicology and ecology are described in detail in the safety data sheets and on the labels, marked and must be observed.
Application temperature	min. + 5°C
Surface temperature	+ 5°C to + 45°C
Relative air humidity	maximum 75% (see the dew point table!)
Laying temperature	160°C - 220°C
Area coverage	At least 60 % when viewed vertically (See also "General notes on the technical information")
Material consumption	The minimum material quantity (without drop-on material) of 3.5 – 4.0 kg/m ² / the specified material quantities specified in accordance with the BAST test certificate may not be undercut.

3 Processing instructions

3.1 Preparing the material and application technique

3.1.1 Preparing the thermoplastic

The empty or partly filled, cooled-off thermal cooker should be preheated for 10 - 15 minutes before filling. The cooker must then be filled up to approx. 1/3 of its capacity with the powder mass including the PE bag and the heating process should be continued. As soon as the agitator can be turned, you can commence the stirring process to comprehensively melt and homogenise the refilled powder mass. Afterwards, the powder mass is continually added into the cooker and melted until the required fill level is achieved. This process enables the shortest possible melting times.

Attention: The thermoplastic is only ready for processing when the specified laying temperature has been reached and the compound has melted homogeneously. The upper limit of the specified laying temperature must not be exceeded, otherwise the binding agent will be damaged or the flash point may be reached. The thermoplastic compound becomes darker (low Qd value) and hardens, it becomes cracked and brittle.

3.1.2 Preparing the application technique

The exact machine settings must be made in accordance with the instructions of the machine manufacturer. Layer thicknesses and drop-on material quantities in accordance with the BAST test certificate must be observed. Ensure that the material and sprinkling drop-on material are distributed evenly over the entire applied surface / strip. The loss of drop-on material to the right / left of the applied strip must be compensated for through the appropriate machine settings.

The theoretical material consumption of material and drop-on material can be found:

- in the respective BAST test certificates
- in table 1 "Turntable road-marking test system (RPA) - BAST test certificates", section 6.2 of this technical information in kg/m²
- in the table "Theoretical material and drop-on material consumption" on our homepage in kg/km of the strip to be marked depending on typical strip widths

3.2 Optimising the processability of the material

The relationship between the laying temperature and the air and surface temperature has a significant influence on the laying viscosity of the thermoplastic and is therefore decisive for the quality of the finished marking, for optimum bead embedding and for the durability (adhesion) of the application as a whole.

Optimal processing conditions for the thermoplastic can therefore only be achieved by adjusting the laying temperature accordingly. The natural cooling of the compound from the cooker through to laying, depending on the application method, must also be factored in.

It is also necessary to conduct regular temperature checks of the melting process both in the cooker and during application.

In general, the following applies: for surface temperatures in the upper limit range, a laying temperature in the lower specified temperature range is sufficient. At surface temperatures in the lower temperature range, the laying temperature must be in the upper temperature range to prevent subsequent cracking.

At air and surface temperatures < 5°C, it is necessary to preheat the surface by means of a hot air dryer in order to achieve good adhesion.

www.swarco.com/rms

SWARCO VESTGLAS GmbH, Rumplerstrasse 12, D-45659 Recklinghausen, Germany

T. +49-2361-6094-0, F. +49-2361-6094-55, E. office.vestglas@swarco.com

Court of jurisdiction: Amtsgericht Recklinghausen, Commercial Register No.: HRB 2180, Tax no.: 340/5933/4421

VAT ID no.: DE813885151

Managing Director: Benjamin Bittner

Attention: Adhesion problems may arise:

- when preheating the surface with an open flame through overheating and damage to the surface layer, or due to rising humidity from the structure of the surface through capillary action.
- through condensation water that forms between the surface and the applied thermoplastic mass depending on the temperature and humidity.

The dew point table can be used to determine the surface temperature at which the air humidity condenses.

An adhesion check is mandatory in the aforementioned cases. Damp surfaces cause strong blistering in the applied thermoplastic, as a result of which the marking peels off and is destroyed due to weather influence (moisture and frost).

Due to its chemical composition, the thermoplastic can be re-plasticised at high air and surface temperatures (warming up). Resulting imprints, e.g. from tyre profiles of parked vehicles in the marking, do not constitute a defect in the sense of the warranty. If necessary, other products (e.g. cold plastic) must be selected in coordination with the customer in such exceptional cases.

4 Surfaces / surface pre-treatment

4.1 General information

The surface must be dry, clean, free of dust, oil, grease, loose particles and other impurities. The surface and any existing old markings must be checked for load-bearing capacity and compatibility with the marking material to be applied. In case of doubt, test markings / adhesion samples must be carried out. If necessary, old markings must be removed using suitable mechanical methods.

4.2 Concrete or cement-bound surfaces

Surface components that impair adhesion, such as fine mortar layers / concrete sludge or subsequently sprayed-on retarders with new concrete surfaces must be removed using suitable methods (e.g. high-pressure water, precision milling, or similar). On newly washed concrete road surfaces (with grit), adhesion problems may still arise that are not caused by the marking substance / primer. We recommend making test markings and to report any concerns that should arise.

Concrete or cement-bound surfaces are generally not ideal surfaces for thermoplastic road marking materials.

Before applying the thermoplastic, the concrete surface must be pre-treated with **primer for thermoplastic**. Ensure that the concrete surface is sufficiently wetted with primer to achieve an optimal adhesion of the thermoplastic. The consumption of primer depends on the porosity of the concrete and can vary, the process must be repeated if necessary. The primer should have sufficient time for the solvent to aerate before the final application of the thermoplastic. The airing time depends on the porosity of the surface and the resulting thickness of the primer layer. 30 minutes should generally be sufficient (ideal: finger test slightly sticky).

The moisture of the concrete must not exceed 4% when marking. We recommend a waiting period of at least 48 hours after rain.

4.3 Bituminous surfaces

All loose elements such as grit must be removed. The existing chemical additives on the surface of new bituminous surfaces (flux oils, oleiferous separating agents for rollers and similar) are principally detrimental to the adhesion of subsequent coats and can lead to a discolouration of the marking. Years of practical experience have shown that thermoplastics are suitable for application on new bituminous surfaces due to similar physical and chemical properties of the binding agent of thermoplastics and bituminous surfaces. In order to rule out possible residual risks (e.g. discolouration), test markings are recommended where necessary. If the result is negative, the new surface should be left under traffic for 4 - 6 weeks before the thermoplastic is laid.

Temporary road markings made from 1-C colours are not recommended since these colour markings represent a separating layer with regards to thermoplastics and reduce adhesion. New bituminous surfaces are usually highly structured and only the colour markings at the tips of the structure are subject to wear, while within the structure the colour is preserved and acts as a separating layer.

If temporary road markings (late autumn with permanently damp surfaces) are necessary, LIMBOROUTE 2-C K809 is recommended for temporary road markings, which was tested and approved in a system with the AGGLOTHERM TS by BAST.

Practical tests of thermoplastic markings on LIMBOROUTE 2-C K809 have shown that sufficient adhesion of both marking substances can only be guaranteed on a freshly applied and ventilated marking made from LIMBOROUTE 2-C K809 as an additional base coat. The application of the final thermoplastic marking (e.g. in spring) thus consists of 2 work steps:

1. approx. 0.3 mm LIMBOROUTE 2-C K809 as additional base coat
2. final thermoplastic marking

Both work steps are carried out in direct succession, while observing the airing time of the LIMBOROUTE 2-C K809.

In the event of temporary road markings made of 1-C HS colours or of LIMBOROUTE 2-C K809 without the aforementioned additional base coat, it must be ensured that the temporary road marking is so worn down that the thermoplastic can thermally bond directly with the bituminous subsurface.

Otherwise the temporary road markings must otherwise be demarcated using suitable technical means.

Older, emaciated bituminous surfaces should be pre-treated with **primer for thermoplastic** to improve adhesion if necessary.

4.4 Paved surfaces

Thermoplastics are not suitable for application on paved surfaces (cracking and adhesion problems).

4.5 Synthetic resin floors

Thermoplastics are not suitable for application on synthetic resin floors. Here, suitable products must be selected under the heading "Hall markings".

5 Application technique

Mechanically with conventional self-driving thermoplastic laying machines with extruder technology for the laying of regular agglomerates. The mechanical or manual laying of stochastic agglomerates with AGGLOTHERM TS is not recommended. Practical experience has shown that the cooling off of the thermoplastic mass in the processing process from thermal cookers to application is too high. The actual laying temperature of the small-sized individual aggregates is usually no longer high enough to ensure a stable thermal connection with the bituminous surface.

The traffic-related properties and the service life of regular agglomerates made of thermoplastic marking systems depend largely on the following factors:

- on the adherence to the specified laying temperature and the aforementioned information
- on the processing of the material quantity (including drop-on material) specified in the BAST test certificate and a good flank formation.
- on a surface covering > 60 % when viewed vertically
- on an optimal distribution and embedding of the quantity and type of drop-on material specified in the BAST test certificate
- on the optimal adjustment of the marking machine and application unit in accordance with the technical specifications of the manufacturer

Note on manual work with templates:

Do not put material adhering to the stencil that has been mixed with release agent back into the cooker.

6 Warranties / test certificates

6.1 Warranties

The traffic-related properties identified in the BAST test certificates result from testing the wear resistance of a marking system under the conditions of the turntable road-marking test system (RPA) at the Federal Highway Research Institute (BAST). The test certificate confirms that a tested marking system meets the minimum requirements for wear resistance (wheel roll-over cycles) specified in the valid ZTV M. It does not represent a warranty of these properties within the specified warranty periods in practice.

A warranty for the traffic-related properties in practice shall be granted within the scope of the currently valid ZTV M and only applies under typical traffic loads caused by free rolling traffic and using the systems recommended and tested by SWARCO Road Marking Systems in compliance with the respective technical information.

Limitation periods for claims for defects (warranty) are ruled out in the following cases:

- exceptionally high wear of the marking on roads with extremely high traffic loads (average daily traffic) caused by rolling traffic, e.g. in conurbations
- exceptional mechanical loads due to: winter road maintenance, tracked vehicles, agricultural traffic and other heavy military equipment, increased radial forces e.g. in curves
- increased load due to changes in traffic routing, e.g. at construction sites

www.swarco.com/rms

SWARCO VESTGLAS GmbH, Rumplerstrasse 12, D-45659 Recklinghausen, Germany

T. +49-2361-6094-0, F. +49-2361-6094-55, E. office.vestglas@swarco.com

Court of jurisdiction: Amtsgericht Recklinghausen, Commercial Register No.: HRB 2180, Tax no.: 340/5933/4421

VAT ID no.: DE813885151

Managing Director: Benjamin Bittner

- insufficient structural condition of a road
- insufficient cleaning of the surface caused by environmental influences (see "General information on the technical information")
- when processing the marking instances in deviation from the specifications of the technical information
- outside the warranty period in accordance with the valid ZTV M
- failure to comply with other specifications of the valid ZTV M (e.g. selection of marking systems, etc.)

Warranties in the system with temporary road markings in accordance with valid ZTV M shall only be assumed if:

- you only use materials from SWARCO Road Marking Systems that have been tested as a marking system as temporary road markings and final markings (see section 4.3)
- the temporary road marking is functional at the time of application with the final marking and adhesion samples that were carried out did not result in any restrictions (adhesion samples of the temporary road marking are mandatory)

6.2 Table 1: Turntable road-marking test system (RPA) - test certificates of BAST

Test certificate no.	Layer thickness	Consumption**		Drop-on material	Traffic-related properties	
	mm	Material	Drop-on material	Designation (deviating designation possible - see test certificate)	New condition	Used condition
		kg/m²	kg/m²			
Regular agglomerates						
2007 1DH 02.01	-	3.7	0.37	SWARCO SOLIDPLUS 30 P21 T14	P7, R5, RW6, Q5, T2*	P7, R3, RW5, Q3
2015 1 DH 02.06	-	3.8	0.45	. SWARCO SOLIDPLUS 10 P21 T14	P7, S0, R5, RW6, Q5, T2	P7, S0, R3, RW4, Q3
Regular agglomerates in system with LIMOBROUTE 2-C K809 as a temporary road marking						
2007 1DH 02.16 K809 AGGLOTHERM TS	0.6	3.7	0.42 0.37	SWARCOLUX P21 T14 M25 SWARCOLUX P21 T14	P7, R5, RW6, Q5, T2*	P7, R3, RW5, Q4

* The specified drying time is a laboratory value and may differ depending on climatic conditions.

**The actual material consumption depends on the application technique, the machine settings and the resulting, actually applied layer thickness, as well as applied drop-on material.

Since 2000, the master sample test for sample uniformity has been carried out at BAST and is usually recorded in the test certificate in section 3.

The basis for the classification of the marking systems into the traffic-related properties in new and used condition was the table "Calculated measurement values" in the appendix "Results for the BAST test number ..." of the respective BAST test certificate:

- **for all colour and reactive systems**
New condition: measured values at 0.01 million wheel roll-over cycles or (no measurement data)
measured values at 0.1 million wheel roll-over cycles
plus the trafficability class
lowest values achieved > 0.01 or 0.1 million wheel roll-over cycles
- **for thermoplastic systems**
New condition: measured values at 0 wheel roll-over cycles
plus the trafficability class
lowest values achieved > 0 wheel roll-over cycles